Röchling

Industrial

Technical Data Sheet

Trovidur® ES FB

Product characteristics

- Easy processing, particulary by sewing or tacking, but also by welding, thermoforming and glueing
- Flame retardant, self-extinguishing after removal of flame
- High impact strength

Product applications

- Bellows
- Mechanical engineering

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	1,41
Water absorption	DIN EN ISO 62	%	0,20
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	48
Elongation at break	DIN EN ISO 527	%	20
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2500
Notched impact strength	DIN EN ISO 179	kJ / m^2	8
Shore hardness	DIN EN ISO 868	scale D	77
Ball indentation hardness	DIN EN ISO 2039-1	MPa	100
Thermal properties			
Thermal conductivity	DIN EN ISO 8302	W / (m * K)	0,16
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	75
Service Temperature		°C	-20 ... +60
Heat deflection temperature	DIN EN ISO 75	°C	70
Coefficient of linear thermal expansion	DIN EN ISO 11359-2	mm/m K	~ 0,075
Electrical properties			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (10^6 Hz)	IEC 60250		0,02
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10^{15}
Surface resistivity	DIN EN 62631-3-2	Ω	>10^{13}

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Information on the REACh regulation can be found in our Product Handling Information Sheets, in our REACh information letter as well as in the SCIP database.

Röchling Industrial SE & Co. KG
Mülheimer Str. 26 • D-53840 Troisdorf/Germany • Tel. +49 2241 4820-0 • Fax +49 2241 4820-100
info@roechling-plastics.com • www.roechling.com/industrial
Date: 29/11/2021 Version: 3.0.0

INTEGRATED MANAGEMENT SYSTEM