

Technical Data Sheet

Matrox[®] X

Product characteristics

- Extremely low coefficient of friction
- Very good abrasion and wear resistance
- High surface hardness

Product applications

- Lining technology

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	>0,98
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Molecular weight	-	10 ⁶ g/mol	~ 9
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1000
Notched impact strength	DIN EN ISO 11542	kJ / m ²	>80
Shore hardness	DIN EN ISO 868	scale D	>65
Wear resistance	Sand-slurry		<80
Sand Slurry	1018 Steel =10		~ 78
Thermal properties			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	150 ... 230
Service temperature, long term	Average	°C	-250 ... 80
Service temperature, short term (max.)	Average	°C	130
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Surface resistivity	DIN EN 62631-3-2	Ω	>10 ¹⁴

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.