

Technical Data Sheet

Fibracon[®] PTFE + 25% Carbon filled

[Characteristics compared to virgin PTFE]

Product characteristics

- Particularly low wear when lubricated with water
- Reduced deformation under load (improved compressive strength)
- Improved thermal and electrical conductivity

Product applications

- Dry, poorly lubricated environments
- Wear resistant seals and gaskets

	Test method	Unit	Guideline Value
General properties			
Bulk Density	ASTM D4894	g/l	600
Specific Gravity	ASTM D4894	-	2.1±0.03
Mechanical properties			
Tensile Strength (Cross Direction)	ASTM D4894	MPa	Min.15
Elongation (Cross Direction)	ASTM D4894	%	Min.90
Ball Hardness	ISO 2039	MPa	45±2
Deformation Under Load	ASTM D621	%	5 - 7
Thermal properties			
Service Temperature		°C	-180 - +260
Service Temperature		°C	-200 to +260
Electrical properties			
Volume Resistivity	ASTM D257	Ωcm	10 ⁴

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.