Röchling

Industrial

Technical Data Sheet

LubX® AST pressed color

Product characteristics

- Antistatic
- Good coefficient of friction
- Available in diverse colours

Product applications

- Materials handling industry
- Pharmaceutical industry
- Food processing industry

	Test method	Unit	Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Moulding Compound PE	DIN ISO 1872-1		UHMW-PE-QCD 35-3-4
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	18
Elongation at yield stress	DIN EN ISO 527	%	14
Tensile modulus of elasticity	DIN EN ISO 527	MPa	800
Impact strength	DIN EN ISO 179	kJ / m^2	65
Shore hardness	DIN EN ISO 868	scale D	60
Sliding properties: partner POM (0,25 m/s - 0,25 MPa)	REP – Tribology – Test		0,19
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 – 135
Coefficient of linear thermal expansion	DIN 53752	10^{-6} / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	≤10^9
Surface resistivity	DIN EN 62631-3-2	Ω	≤10^9

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values

Röchling Industrial SE & Co. KG
Röchlingstr. 1 • D-49733 Haren/Germany • Tel. +49 5934 701-0 • Fax +49 5934 701-299
info@roechling-plastics.com • www.roechling.com/industrial
Date: 08/07/2020 Version: 2.0.0

INTEGRATED MANAGEMENT SYSTEM