Röchling

Industrial

Technical Data Sheet

SustaPEEK MG green

Product characteristics

- High purity
- Very good sterilisation resistance
- ISO 10993-5 tested on semi-finished product

Product applications

- Medical engineering
- Pharmaceutical industry
- Precision mechanics

	Test method	Unit	Value
Propriétés générales			
Density	DIN EN ISO 1183-1	g / cm^3	1,38
Water absorption	DIN EN ISO 62	%	0,2
Inflammabilité (Épaisseur 3 mm / 6 mm)	UL 94		V0 / V0
Propriétés mécaniques			
Limite d'élasticité	DIN EN ISO 527	MPa	110
Élongation	DIN EN ISO 527	%	15
Module d'élasticité	DIN EN ISO 527	MPa	4000
Shore hardness	DIN EN ISO 868	scale D	88
Propriétés thermiques			
Température de fusion	ISO 11357-3	°C	343
Thermal conductivity	DIN 52612-1	W / (m * K)	0,25
Thermal capacity	DIN 52612	kJ / (kg * K)	1,34
Coefficient de dilatation thermique linéaire	DIN 53752	10^{-6} / K	50
Température de service, à long terme	Average	°C	-60 ... 250
Température de service, court terme (max.)	Average	°C	310
Heat deflection temperature	DIN EN ISO 75, Verf. A, HDT	°C	152
Propriétés électriques			
Dielectric constant	IEC 60250		3,2
Dielectric dissipation factor (50 Hz)	IEC 60250		0,001
Volume resistivity	DIN EN 62631-3-1	Ω * cm	4,9 * 10^{16}
Résistivité de surface	DIN EN 62631-3-2	Ω	10^{18}
Dielectric strength	IEC 60243	kV / mm	20

This material is not intended for the use in medical products that remain for more than 24 hours in the human body or are intended to remain in contact with internal human tissue or blood for more than 24 hours. The short-term maximum application temperature only applies to very low mechanical stress for a few hours. The long-term maximum application temperature is based on the thermal ageing of plastics by oxidation, resulting in a decrease of the mechanical properties. This applies to an exposure to temperatures for at least 5.000 hours causing a 50% loss of the tensile strength from the original value (measured at room temperature). This value says nothing about the mechanical strength of the material at high application temperatures. In case of thick-walled parts, only the surface layer is affected by oxidation from high temperatures. With the addition of antioxidants, a better protection of the surface layer is achieved. In any case, the center area of the material remains unaffected. The minimum application temperature is basically influenced by possible stress factors like impact and/or shock under application. The values stated refer to an minimum degree of impact stress. The electrical properties as stated result from measurements on natural, dry material. With other colours (in particular black) or saturated material, there may be clear differences in the electrical properties. The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. They serve as information about our products and are presented as a guide to choose from our range of materials. This, however, does not include an assurance of specific properties or the suitability for particular application purposes that are legally binding. Since the properties also depend on the dimension of the semi-finished products and the degree of crystallization (e.g. nucleating by pigments), the actual values of the properties of a particular product may differ from the indicated values.

Röchling Industrial Lahnstein SE & Co. KG
Sustaplast-Str. 1 • D-56112 Lahnstein/Germany • Tel. +49 2621 693-0 • Fax +49 2621 693-170
info@sustaplast.de • www.roechling.com/industrial
Date: 14/09/2017 Version: 2.0.0

INTEGRATED MANAGEMENT SYSTEM