

Technical Data Sheet

Polystone® D natural

Product characteristics

- Good mechanical properties
- Very wear-, cutting and scratch resistant
- Physiologically safe

Product applications

- Environment and disposal technology
- Cutting boards
- Sports and leisure industry

	Test method	Unit	Value
Propriétés générales			
Density	DIN EN ISO 1183-1	g / cm ³	>0,95
Water absorption	DIN EN ISO 62	%	<0,01
Inflammabilité (Épaisseur 3 mm / 6 mm)	UL 94		HB
Propriétés mécaniques			
Limite d'élasticité	DIN EN ISO 527	MPa	>27
Élongation	DIN EN ISO 527	%	>50
Module d'élasticité	DIN EN ISO 527	MPa	>1200
Shore hardness	DIN EN ISO 868	scale D	65
Propriétés thermiques			
Température de fusion	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient de dilatation thermique linéaire	DIN 53752	10 ⁻⁶ / K	150 ... 230
Température de service, à long terme	Average	°C	-100 ... 80
Température de service, court terme (max.)	Average	°C	80
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
Propriétés électriques			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10 ⁶ Hz)	IEC 60250		0,0002
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 ¹⁴
Résistivité de surface	DIN EN 62631-3-2	Ω	>10 ¹⁴
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.