Röchling

Industrial

Technical Data Sheet

Robaflow®

Product characteristics

- Good mechanical properties
- Very wear, cutting and scratch resistant
- Physiologically safe

Product applications

- Paper industry / headbox vanes

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	0,96
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	27
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength	DIN EN ISO 179	kJ / m^2	no break
Shore hardness	DIN EN ISO 868	scale D	65
Thermal properties			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,4
Thermal capacity	DIN 52612	kJ / (kg * K)	1,9
Coefficient of linear thermal expansion	DIN 53752	10^{-6} / K	150 - 230
Service temperature, long term	Average	°C	-100 ... 80
Service temperature, short term (max.)	Average	°C	100
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
Electrical properties			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10^6 Hz)	IEC 60250		0,0002
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10^{14}
Surface resistivity	DIN EN 62631-3-2	Ω	>10^{14}
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	45

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial Oepping GmbH & Co. KG
Röchlingstraße 1 • A-4151 Oepping/Austria • Tel. +43 7289 4611-0 • Fax +43 7289 4611-9900
robaproducts@roechling.com • www.roechling.com/industrial
Date: 28/04/2020 Version: 2.0.0

INTEGRATED MANAGEMENT SYSTEM