

Technical Data Sheet

Robalon® E

Product characteristics

- Good chemical resistance
- Antistatic Surface
- Electrically conductive

Product applications

- Industrie du transport
- Mining
- Mechanical engineering

	Test method	Unit	Value
Propriétés générales			
Density	DIN EN ISO 1183-1	g / cm ³	0,94
Water absorption	DIN EN ISO 62	%	<0,01
Inflammabilité (Épaisseur 3 mm / 6 mm)	UL 94		HB/HB
Molecular weight		g / mol	9,20 * 10 ⁶
Color			black
Propriétés mécaniques			
Limite d'élasticité	DIN EN ISO 527	MPa	16
Élongation	DIN EN ISO 527	%	>270
Module d'élasticité	DIN EN ISO 527	MPa	600
Notched impact strength	DIN EN ISO 179/1eA	kJ / m ²	>90
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	63
Compression - compression set	23°C, 2N/mm ² , 1h	%	~2
Compression - compression set	80°C, 10N/mm ² , 56h	%	~20
Propriétés thermiques			
Melting temperature	DIN EN ISO 3146	°C	135
Thermal conductivity	DIN EN ISO 8302	W / (m * K)	0,41
Thermal capacity	DIN 51005	kJ / (kg * K)	1,84
Coefficient de dilatation thermique linéaire	DIN 53752	10 ⁻⁶ / K	200
Température de service, à long terme	Average	°C	-200 ... 80
Température de service, court terme (max.)	Average	°C	110
Propriétés électriques			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	10 ⁴
Résistivité de surface	DIN EN 62631-3-2	Ω	<10 ⁷
Comparative tracking index	IEC 60112		600

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.