Röchling

Industrial

Technical Data Sheet

LubX® CV

Product characteristics

- Excellent sliding properties even at higher load
- Excellent dry-running properties
- Food compliant according to 10/2011/EU, 1935/2004/EC, FDA

Product applications

- Materials handling industry
- Automation

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	0,94
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
Non-toxicity			+
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	19
Elongation at break	DIN EN ISO 527	%	>250
Tensile modulus of elasticity	DIN EN ISO 527	MPa	800
Notched impact strength	DIN EN ISO 179	kJ / m^2	no break
Shore hardness	DIN EN ISO 868	scale D	60
Sliding properties: partner POM (0,5 m/s - 0,5 MPa)	REP – Tribology – Test		0,13
Thermal properties			
Melting temperature	ISO 11357-3	°C	133 – 135
Coefficient of linear thermal expansion	DIN 53752	10^{-6} / K	150 - 230 (*)
Service temperature, long term	Average	°C	-150 ... 80 (*)
Service temperature, short term (max.)	Average	°C	130 (*)
Electrical properties			
Volume resistivity	DIN EN 62631-3-1	Ω * cm	$>10^{15}$
Surface resistivity	DIN EN 62631-3-2	Ω	$>10^{14}$

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale. (*) literature values

Röchling Industrial SE & Co. KG
Röchlingstr. 1 • D-49733 Haren/Germany • Tel. +49 5934 701-0 • Fax +49 5934 701-299
info@roechling-plastics.com • www.roechling.com/industrial
Date: 08/07/2020 Version: 2.0.0

INTEGRATED MANAGEMENT SYSTEM