Röchling

Industrial

Technical Data Sheet

Trovidur® W 1014

Product characteristics

- High chemical resistance
- Good glueability
- Weldable and hot-formable

Product applications

- Seals
- Cutting boards
- Compensators

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	1,22
Water absorption	DIN EN ISO 62	%	0,2
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	300
Shore hardness	DIN EN ISO 868	scale A	66
Thermal properties			
Service Temperature		°C	-10 ... +60

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Röchling Industrial SE & Co. KG
Mülheimer Str. 26 • D-53840 Troisdorf/Germany • Tel. +49 2241 4820-0 • Fax +49 2241 4820-100
info@roechling-plastics.com • www.roechling.com/industrial
Date: 01/12/2021 Version: 2.0.0

INTEGRATED MANAGEMENT SYSTEM