

Technical Data Sheet

Trovidur® W 1590

Product characteristics

- Very good electrical insulation properties
- Good glueability
- Weldable and hot-formable

Product applications

- Seals
- Compensators
- Packings

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,22
Water absorption	DIN EN ISO 62	%	0,2
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	300
Shore hardness	DIN EN ISO 868	scale A	73
Thermal properties			
Service Temperature		°C	-10 ... +60

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Information on the REACh regulation can be found in our Product Handling Information Sheets, in our REACh information letter as well as in the SCIP database.