Röchling

Industrial

Technical Data Sheet

Trovidur® W 1590

Product characteristics

- Very good electrical insulation properties
- Good glueability
- Weldable and hot-formable

Product applications

- Seals
- Compensators
- Packings

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	1,22
Water absorption	DIN EN ISO 62	%	0,2
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	300
Shore hardness	DIN EN ISO 868	scale A	73
Thermal properties			
Service Temperature		°C	-10 ... +60

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.

Information on the REACh regulation can be found in our Product Handling Information Sheets, in our REACh information letter as well as in the SCIP database.

Röchling Industrial SE & Co. KG
Mülheimer Str. 26 • D-53840 Troisdorf/Germany • Tel. +49 2241 4820-0 • Fax +49 2241 4820-100
info@roechling-plastics.com • www.roechling.com/industrial
Date: 01/12/2021 Version: 3.0.0