Röchling

Industrial

Technical Data Sheet

Fibracon® PTFE + 10% Polyimide

Product characteristics

- High wear resistance
- Good dimensional stability

Product applications

- Seals
- Valve seats
- Bearings

	Test method	Unit	Guideline Value
General properties			
Density	ASTM 4894	g/cm^3	2.02
Mechanical properties			
Hardness	Needle	Shore D	61
Tensile Strength (23°C)	ASTM 4894	MPa	24
Elongation at Break	ASTM 4894	%	260
Thermal properties			
Service Temperature		°C	-200 to +260

This data provides typical values on a small selection of properties of the material and should only be used as a guide to the generic material performance.

Röchling Industrial (UK) Ltd.
Bowden Hey Road, Chapel-en-le-Frith, High Peak, SK23 0QZ, UK
T: +44 (0) 1298 811800 F: +44 (0) 1298 811801 E: sales@roechling-fibracon.co.uk - www.roechling.com/uk/industrial
Date: 29/04/2020 Version: 3.0.0