Röchling

Industrial

Technical Data Sheet

Robaseal® A

Product characteristics

- Excellent dry-running properties
- Low thermal expansion
- Excellent sliding behaviour

Product applications

- Pulp- & Paper industry
- Suction roll / sealing strip and end deckles

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	1,57
Water absorption	DIN EN ISO 62	%	0,05
Coefficient of friction (against steel)	internal method: 2m/s; 1MPa	-	0,125
Mechanical properties			
Elongation at break	DIN EN ISO 527	%	0,76
Tensile modulus of elasticity	DIN EN ISO 527	MPa	14.700
Tensile strength	DIN EN ISO 527	MPa	66
Shore hardness	DIN EN ISO 868 / 15 sec	scale D	~76
Flexural Strength		MPa	93
Thermal properties			
Thermal conductivity	DIN 52612-1	W / (m * K)	10,4
Coefficient of linear thermal expansion	DIN 53752	10^{-6} / K	13,6
Service temperature, long term	Average	°C	120

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Röchling Industrial Oepping GmbH & Co. KG
Röchlingstraße 1 • A-4151 Oepping/Austria • Tel. +43 7289 4611-0 • Fax +43 7289 4611-9900
robaproducts@roechling.com • www.roechling.com/industrial
Date: 28/04/2020 Version: 2.0.0