Röchling

Industrial

Technical Data Sheet

Robatube PVC

Product characteristics

- Good chemical resistance
- Good stroke characteristics
- High temperature resistance

Product applications

- Pulp- & Paper industry
- Suction roll / sealing strip and end deckles

	Test method	Unit	Guideline Value
General properties			
Density	DIN EN ISO 1183-1	g / cm^3	1,21
Water absorption	DIN EN ISO 62	%	0,016
Color			violet
Storage period in years			~ 5
Mechanical properties			
Shore hardness	DIN EN ISO 868	scale A	58
Tensile strength	internal method	MPa	11
Max. pressure	internal method	bar	2,0
Burst pressure	internal method	bar	> 2,5
Elongation at break	internal method	%	400
Thermal properties			
Service temperature, long term	Average	°C	-45 ... 70

The burst pressure was determined at a temperature of 20°C (locular).

The data given are standard values which are based on our experience & previous technical studies. These values are influenced by the design, processing conditions and environmental influences out of our control. The sustainability of the material for a given application is the responsibility of the user. Typing and printing errors reserved.

Röchling Industrial Oepping GmbH & Co. KG
Röchlingstraße 1 • A-4151 Oepping/Austria • Tel. +43 7289 4611-0 • Fax +43 7289 4611-9900
robaproducts@roechling.com • www.roechling.com/industrial
Date: 28/04/2020 Version: 2.0.0